

# Opus™ Paver



## Elegant and Versatile

This paver is perfect for borders or for combinations with the paver of your choice.

## Qualities and Characteristics

- Choice of three colors
- 2 3/8" thick.
- 3 different designs
- Installation on its own (runner, herringbone, mosaic) or combined with your choice of paver
- Natural finish
- Blends well with Appalachian or Sutton wallstones.



# BOLDUC

Fashioned in line with nature!

# Opus™ Paver

## COLORS



Sandy Gray



Anthracite Gray



Sandhill Beige

NOTE:  
We recommend that you use actual samples to make your final choice.

## VARIATION IN PAVER LENGTH

HEIGHT X WIDTH X LENGTH		NUMBER OF PIECES	
in.	cm	/ft <sup>2</sup>	/m <sup>2</sup>
2 3/8 x 3 15/16 x 7 7/8	6 x 10 x 20	4.13	44.4



## DIMENSIONAL TOLERANCES †

Permissible dimensional tolerances under the CSA A231.2 standard are as follows:

Length:	±1/16 in (-1 mm to +2 mm)
Width:	±1/16 in (-1 mm to +2 mm)
Height:	±1/8 in (±3 mm)

## THICKNESS: 2 3/8 in. (6 cm)

## PHYSICAL CHARACTERISTICS †

COMPRESSIVE STRENGTH**	DURABILITY TO FREEZE-THAW CYCLES WITH UTILISATION OF DE-ICING SALTS**	WATER ABSORPTION
7250 psi (50 MPa) after 28 days' conditioning	Maximum loss of mass in saline solution (NaCl 3%): • 0.74oz/ft <sup>2</sup> (225 g/m <sup>2</sup> ) after 28 cycles • 1.64oz/ft <sup>2</sup> (500 g/m <sup>2</sup> ) after 49 cycles	5% maximum

## INSTALLATION PATTERNS

### Runner pattern



### Herringbone pattern



† Laboratory test reports available on request  
\*\* Tested under CSA A231.2 standard



**BOLDUC**  
Concrete product manufacturer

1358-2nd Street, Industrial Park, P.O. Box 608,  
Sainte-Marie, Beauce, Québec, Canada G6E 3B8

Sainte-Marie: (418) 387-2634  
Québec: (418) 692-0855  
Toll free Canada: 1-800-463-8966  
Toll free USA: 1-800-603-5567  
Fax: (418) 387-6438  
www.bolduc.us  
info@bolduc.us