

# Supra Acadia® Paver



## Refinement and Relaxation

With its contemporary elegance, this large-size paver adds style to any layout.

## Qualities and Characteristics

- Choice of four colors
- 3 1/8" thick
- Three different paver shapes
- Installation can be modular or in runner patterns
- Natural finish
- Blends well with Appalachian, Sutton or Laurentian wallstones



# BOLDUC

Fashioned in line with nature!

# Supra Acadia® Paver

## COLORS



Sandy Gray



Ashen Beige



Sandhill Beige




Indiana Beige

NOTE:


We recommend that you use actual samples to make your final choice.

## Installation Patterns

Runner



Modular



## VARIATION IN PAVER LENGTH

	HEIGHT X WIDTH X LENGTH		NUMBER OF PIECES	
	in.	cm	/ft <sup>2</sup>	/m <sup>2</sup>
1.	3 1/8 x 5 7/8 x 11 13/16	8 x 15 x 30	1.03	11.1
2.	3 1/8 x 11 13/16 x 11 13/16	8 x 30 x 30		
3.	3 1/8 x 11 13/16 x 17 3/4	8 x 30 x 45		



## DIMENSIONAL TOLERANCES †

Permissible dimensional tolerances under the CSA A231.2 standard are as follows:

Length:	±1/16 in (-1 mm to +2 mm)
Width:	±1/16 in (-1 mm to +2 mm)
Height:	±1/8 in (±3 mm)

## THICKNESS: 3 1/8 in. (8 cm)

## PHYSICAL CHARACTERISTICS †

COMPRESSIVE STRENGTH**	DURABILITY TO FREEZE-THAW CYCLES WITH UTILISATION OF DE-ICING SALTS**	WATER ABSORPTION
7250 psi (50 MPa) after 28 days' conditioning	Maximum loss of mass in saline solution (NaCl 3%) : • 0.74oz/ft <sup>2</sup> (225 g/m <sup>2</sup> ) after 28 cycles • 1.64oz/ft <sup>2</sup> (500 g/m <sup>2</sup> ) after 49 cycles	5% maximum

## INSTALLATION PATTERNS



† Laboratory test reports available on request

\*\* Tested under CSA A231.2 standard



**BOLDUC**  
Concrete product manufacturer

1358-2nd Street, Industrial Park, P.O. Box 608,  
Sainte-Marie, Beauce, Québec, Canada G6E 3B8

Sainte-Marie: (418) 387-2634  
 Québec: (418) 692-0855  
 Toll free Canada: 1-800-463-8966  
 Toll free USA: 1-800-603-5567  
 Fax: (418) 387-6438  
 www.bolduc.us  
 info@bolduc.us