

Supra Acadia® Paver



Refinement and Relaxation

With its contemporary elegance, this large-size paver adds style to any layout.

Qualities and Characteristics

- Choice of four colors
- 3 1/8" thick
- Three different paver shapes
- Installation can be modular or in runner patterns
- Natural finish
- Blends well with Appalachian, Sutton or Laurentian wallstones



BOLDUC

Fashioned in line with nature!

Supra Acadia® Paver

COLORS



Sandy Gray



Ashen Beige



Sandhill Beige




Indiana Beige

NOTE:


We recommend that you use actual samples to make your final choice.

Installation Patterns

Runner



Modular



VARIATION IN PAVER LENGTH

	HEIGHT X WIDTH X LENGTH		NUMBER OF PIECES	
	in.	cm	/ft ²	/m ²
1.	3 1/8 x 5 7/8 x 11 13/16	8 x 15 x 30	1.03	11.1
2.	3 1/8 x 11 13/16 x 11 13/16	8 x 30 x 30		
3.	3 1/8 x 11 13/16 x 17 3/4	8 x 30 x 45		



DIMENSIONAL TOLERANCES †

Permissible dimensional tolerances under the CSA A231.2 standard are as follows:

Length:	±1/16 in (-1 mm to +2 mm)
Width:	±1/16 in (-1 mm to +2 mm)
Height:	±1/8 in (±3 mm)

THICKNESS: 3 1/8 in. (8 cm)

PHYSICAL CHARACTERISTICS †

COMPRESSIVE STRENGTH**	DURABILITY TO FREEZE-THAW CYCLES WITH UTILISATION OF DE-ICING SALTS**	WATER ABSORPTION
7250 psi (50 MPa) after 28 days' conditioning	Maximum loss of mass in saline solution (NaCl 3%) : • 0.74oz/ft ² (225 g/m ²) after 28 cycles • 1.64oz/ft ² (500 g/m ²) after 49 cycles	5% maximum

INSTALLATION PATTERNS



† Laboratory test reports available on request

** Tested under CSA A231.2 standard



BOLDUC
Concrete product manufacturer

1358-2nd Street, Industrial Park, P.O. Box 608,
Sainte-Marie, Beauce, Québec, Canada G6E 3B8

Sainte-Marie: (418) 387-2634
 Québec: (418) 692-0855
 Toll free Canada: 1-800-463-8966
 Toll free USA: 1-800-603-5567
 Fax: (418) 387-6438
 www.bolduc.us
 info@bolduc.us