

# Linia™ Paver




## Simplicity and Refinement!

With its straight lines and plane surfaces, this paver is perfectly suited for contemporary and classical décors. Its thickness gives it the versatility to be used in a variety of applications, including driveways.

### Characteristics

- 4 inches (10 cm) thick
- Regular finish
- Choice of 2 solid and contrasting colours



# BOLDUC

Fashioned in line with nature!

# Linia™ Paver

COLORS



Gray



Black

NOTE:

We recommend that you make your final choice with actual samples.

When installing Gray or Black pavers, we recommend covering them with a membrane to protect from dirt and grime. Walk on the protective membrane during installation to prevent staining or spotting.


We also recommend using a Teflon-coated vibrating plate on pavers during installation, to protect stone surfaces.

Once pavers have been installed and properly cleaned, we recommend applying a sealer for easier maintenance.

GEOMETRIC CHARACTERISTICS

NOMINAL DIMENSIONS

HEIGHT X WIDTH X LENGTH	NUMBER OF PIECES		
	in.	cm	/ft <sup>2</sup>
1. 3 <sup>15/16</sup> x 3 <sup>15/16</sup> x 17 <sup>3/4</sup>	10 x 10 x 45	2,06	22,2
2. 3 <sup>15/16</sup> x 7 <sup>7/8</sup> x 23 <sup>5/8</sup>	10 x 20 x 60	0,77	8,3



DIMENSIONAL TOLERANCES †

The permitted dimensional tolerances prescribed by in the CSA A231.2, CSA A231.1 standard are the following:  
 Length : -1/32 in. to + 5/64 in. (-1 mm to +2 mm)  
 Width : -1/32 in. to + 5/64 in. (-1 mm to +2 mm)  
 height : ± 1/8 in. (± 3 mm)

WEIGHT OF PAVERS: 48.1 lb/sq. ft. (235 kg/m<sup>2</sup>)

PHYSICAL CHARACTERISTICS †

COMPRESSIVE STRENGTH*	DURABILITY TO FREEZE-THAW CYCLES WITH UTILISATION IN SALINE SOLUTION**	WATER ABSORPTION
7250 Psi (50 Mpa)	Maximum loss of initial weight in saline solution (NaCl 3%): • 0.74oz / pi2 (225 g/m2) after 28 cycles • 1.64oz / pi2 (500 g/m2) after 49 cycles	5% maximum

SPECIFICATION CLAUSE

**SPEC. NOTE:** Include the following article in part 2- Products of section 32 14 13-Precast Concrete Pavers. It prescribes the choice for BOLDUC Pavers for landscaping purposes. It should describes the geometric and physical characteristics and, also, the type, the dimensions, the color and the finish.

PART 2 - PRODUCTS

2.1 Precast Concrete Pavers

.1 Precast concrete pavers complying with CSA A231.2 and the following prescriptions.

.2 Linia pavers as supplied by BOLDUC.

.1 Thickness: 3<sup>15/16</sup> in. (10 cm)

.2 Nominal Dimensions: \_\_\_\_\_

.3 Color: \_\_\_\_\_

.4 Texture: Regular finish

INSTALLATION

Refer to the technical service or to Bolduc's website at [www.bolduc.ca](http://www.bolduc.ca) to obtain the model specification, installation guide or any other technical information.

† Copies of lab tests are available upon request.

\* Tests performed as per CSA A231.2



**BOLDUC**  
Concrete product manufacturer

1358-2nd Street, Industrial Park,  
Sainte-Marie, Beauce, Québec, Canada G6E 1G8

Sainte-Marie: (418) 387-2634  
 Toll free Canada: 1-800-463-8966  
 Toll free USA: 1-800-603-5567  
 Fax: (418) 387-6438  
[www.bolduc.ca](http://www.bolduc.ca)  
[www.bolduc.us](http://www.bolduc.us)  
[info@bolduc.ca](mailto:info@bolduc.ca)